

Product Code	VLT %	VLR %	UV Transmission %	Summer U-Factor W/m2K	Winter U-Factor W/m2K	Shading Coefficient	Solar Energy Transmission %	Solar Energy Reflectance %	Solar Energy Absorption %	TSER %	* IGDB ID#
Nature Green 50	54.9	14.9	<1	5.35	5.90	0.64	42.3	15.0	42.7	45.0	1715
Nature Green 60	70.0	8.3	<1	5.64	6.19	0.82	60.8	7.6	31.6	29.0	1716
Crystal Green 30	36.3	30.8	<1	5.05	5.62	0.45	25.6	29.5	44.9	62.0	1728
Crystal Green 50	57.5	15.2	<1	5.35	5.90	0.65	43.1	14.4	42.5	44.0	1729
Crystal Blue 55	57.9	12.0	<1	5.39	5.94	0.69	47.6	11.7	40.7	40.0	1731
Jasper Gold 50	54.0	17.5	<1	5.32	5.87	0.63	42.9	17.9	39.2	46.0	1720
Lite Pearl 30	29.0	18.3	<1	5.05	5.62	0.47	25.0	22.7	52.3	60.0	1718
Lite Pearl 60	61.0	14.0	<1	5.40	5.95	0.69	49.1	14.5	36.4	40.0	1719
Lavender 50	55.3	14.1	<1	5.28	5.82	0.65	43.2	14.8	42.0	44.0	1755
CS 70	36.0	10.0	<1	5.37	5.94	0.58	35.0	16.0	49.0	50.0	1700
CS 60	49.2	11.7	<1	5.39	5.94	0.65	42.8	12.5	44.7	44.0	1730
MX 10	6.9	15.6	<1	5.22	5.76	0.48	22.3	15.9	61.8	59.0	1749
MX 20	21.4	21.4	<1	5.10	5.67	0.48	25.6	21.5	52.9	59.0	1717
MX 30	29.9	24.3	<1	5.04	5.61	0.47	26.3	23.6	50.1	59.0	1714
HPR 35GN	33.6	10.1	<1	5.19	5.73	0.55	30.7	14.2	55.1	53.0	1753
GS 10	8.0	5.7	<1	5.37	5.90	0.56	28.0	9.2	62.8	52.0	1747
GS 15	15.8	6.1	<1	5.40	5.93	0.57	29.3	8.8	61.9	51.0	1744
GS 25	26.7	9.0	<1	5.49	6.03	0.61	35.1	8.4	56.5	47.0	1745
GS 35	36.9	7.4	<1	5.43	5.96	0.64	39.3	9.1	51.6	45.0	1754
SL 50	53.6	21.1	<1	5.25	5.81	0.60	39.7	19.5	40.8	48.0	1723
SL 60	59.7	16.6	<1	5.35	5.90	0.66	44.9	15.5	39.6	43.0	1743
Lite 70	69.9	9.6	<1	5.51	6.04	0.79	58.0	8.8	33.2	32.0	1752
R 20S	24.0	51.0	<1	4.97	5.56	0.31	18.0	49.0	33.0	73.0	1709
R 35S	42.3	28.3	<1	4.94	5.52	0.50	31.3	26.1	42.6	57.0	1727
R 10SG	5.0	48.0	<1	5.06	5.64	0.27	10.0	45.0	45.0	77.0	1708
R 8SB	3.8	49.9	<1	5.04	5.61	0.25	7.9	45.0	47.1	79.0	1724
R 15G	8.6	11.7	<1	5.24	4.67	0.33	10.2	25.2	64.6	67.0	1751
R 15B	12.4	18.4	<1	4.67	5.24	0.33	11.9	28.3	59.8	72.0	1748
R 15GO	16.9	40.9	<1	4.64	5.21	0.30	12.4	38.9	48.7	74.0	1750